

Leghe standard "al Pb"

Designazione lega	Cu	Ni	Sn	Pb	Fe	Al	Si	Mn	As
CuZn35Pb1 CW600N	62.5÷64.0	0.3	0.1	0.8 ÷ 1.6	0.1	0.05	-	-	-
CuZn36Pb2As CW602N	61.0÷63.0	0.3	0.1	1.7 ÷ 2.8	0.1	0.05	-	0,1	0.02÷0.15
CuZn36Pb3 CW603N	60.0÷62.0	0.3	0.2	2.5 ÷ 3.5	0.3	0.05	-	-	-
CuZn37Pb1 CW605N**	61.0÷62.5	0.3	0.3	0.8 ÷ 1.6	0.3	0.05	-	-	-
CuZn37Pb2 CW606N	61.0÷62.0	0.3	0.2	1.6 ÷ 2.5	0.2	0.05	-	-	-
CuZn38Pb1 CW607N	60.0÷61.0	0.3	0.2	0.8 ÷ 1.6	0.2	0.05	-	-	-
CuZn38Pb2 CW608N	60.0÷61.0	0.3	0.2	1.6 ÷ 2.5	0,2	0.05	-	-	-
SPM - Lega CG 13	59.5÷61.0	0.1	0.3	1.5÷2.5	0.3	0.05			
CuZn39Pb1 CW611N**	59.0÷60.0	0.3	0.3	0.8 ÷ 1.6	0.3	0.05	-	-	-
CuZn39Pb2 CW612N	59.0÷60.0	0.3	0.3	1.6 ÷ 2.5	0.3	0.05	-	-	-
CuZn39Pb2Sn CW613N	59.0÷60.0	0,3	0.2÷0.5	1.6 ÷ 2.5	0.4	0.1	-	-	-
CuZn39Pb3 CW614N	57.0÷59.0	0.3	0.3	2.5 ÷ 3.5	0.3	0,05	-	-	-
CuZn40Pb1Al CW616N	57.0÷59.0	0.2	0.2	1.0 ÷ 2.0	0.2	0.05÷0.30	-	-	-
CuZn40Pb2 CW617N	57.0÷59.0	0.3	0.3	1.6 ÷ 2.5	0.3	0.05	-	-	-

Leghe Speciali e/o "senza Pb"

Designazione lega	Cu	Ni	Sn	Pb	Fe	Al	Si	Mn	As
CuZn36 CW507L	63.5÷65.5	0,3	0.1	0,05	0,05	0,02	-	-	-
CuZn37 CW508L	62.0÷64.0	0,3	0.1	0,1	0,1	0,05	-	-	-
63 As Lega CG 38	62.0÷64.0	0,3	0.1	0,1	0,1	0,05			0.05÷0.08
CuZn40 CW509L	59.0÷61.5	0.3	0.2	0.2	0.2	0.05	-	-	-
CuZn42 CW510L	57.0÷59.0	0.3	0.3	0.2	0.3	0,05	-	-	-
CuZn38As CW511L	61.5÷63.5	0.3	0.1	0.2	0.1	0.05	-	-	0.02÷0.15
CuZn39Sn1 CW719R	59.0÷61.0	0.2	0.5÷1.0	0.2	0.1	-	-	-	-
CuZn40Si CF724R	58.5÷61.5	-	0.2	0.02	0.25	0.01	0.2÷0.4	-	-
C46500 Naval Brass, Arsenical	59.0÷62.0	-	0.50÷1.0	0.20	0.10	-	-	-	0.02÷0.06
C67300 Manganese Bronze	58.0÷63.0	0.25	0.30	0.40÷3.0	0.50	0.25	0.5÷1.5	2.0÷3.5	-
CuZn37Mn3Al2PbSi CW713R	57.0÷59.0	1.0	0.4	0.2÷0.8	1.0	1.3÷2.3	0.3÷1.3	1.5÷3.0	-
CuZn35Pb1.5AlAs CW625N**	62.0÷64.0	0.2	0.3	1.2 ÷ 1.6	0.3	0.5÷0.7	-	0,1	0.02÷0.15
CuZn33Pb1.5AlAs CW626N**	64.0÷66.0	0.2	0.3	1.2 ÷ 1.7	0.3	0.8÷1.0	-	0,1	0.02÷0.15

** Leghe non presenti nella revisione delle norme del 2011 o presenti con limiti differenti dagli attuali